

# TITAN LAM 150 | GLOSS TLG-150

Conformable high gloss overlam with hydrophobic topcoat for powervehicle graphics.

## FACE FILM

Hybrid PVC, gloss clear

Thickness (µm)	150	
Tensile strength (N/mm <sup>2</sup> )	>15	DIN EN ISO 527
Elongation at break (%)	>150	DIN EN ISO 527

## ADHESIVE

Clear solvent-based acrylic, permanent

Thickness (µm)	25	
Adhesion to steel		FINAT FTM 1
20 minutes (180°) N/25mm	13	
24 hours (180°) N/25mm	18	

## RELEASE LINER

Clear PET liner

Thickness (µm)	75
----------------	----

## PROTECTION FILM

Thickness (µm)	75
----------------	----

## PRODUCT APPLICATION

Application method	Cold lamination (<30°C)
Application temperature (°C)	10 to 30
Service temperature (°C)	-20 to 70

## DURABILITY

Shelf life (months)	12	
Outdoor durability (years)	6	Northern-EU climate, vertical exposure

## ROLL SIZES

1370mm x 15m

Fourbases BV guarantees the material for twelve months from the date of final invoice. The shelf life of our material depends on storage conditions. The end user should store the material in the original boxes or in equivalent boxes, away from direct sunlight, at a temperature of 21°C and 50% relative humidity. Fourbases BV guarantees that the products are free from defects in workmanship or defects in TITAN material, provided they are stored properly. At its sole discretion, Fourbases BV may either: (1) replace all or part of the materials, or (2) issue a credit note for the value of the defective portion. All quoted data values are typical and should not be used as a basis to consider the product defective if measured values differ.